

DATA SHEET

Bouche Pores / Pore Sealant

Description

Harmony Pore Sealant is a water-based primer/pore sealant which is recommended for use prior to the application of Harmony Optimum Lacquer.

Characteristics

Type: single component water based primer/pore sealant

Colours: White

Dosage: 1 l = 10 – 12m² in a single coat

Storage: 12 months in unopened original packaging, stored in a dry and frost-free location.

Guarantee: Manufacturer's liability

Tools & Cleaning

Lacquer roller, paint gun, sprayer, protective gloves, tarpaulin, paint tray.

Clean tools in water after use.

Preparation

The base surface must be resistant, sound, solid, clean, dry and free of humidity.

Use Harmony neutral agent or Harmony degreaser for any cleaning required (to remove grease, oil etc).

Application

Application must be completed within a temperature range of 5° - 25°.

Coverage: 1 litre/10 - 12m².

Apply a thin and uniform film in a ratio of 1 litre per 10 m², applied in a single coat. Where a lacquer roller is used, apply a crosswise action to ensure the effective spreading of pore sealant. Do not create any excess thickness.

Where a large area is to be covered, use the 250 or 500 mm PermaPro special floor nozzle, or the PermaPro paint gun.

On an anhydrite screed or smoothed concrete, it is recommended to moisten the base slightly

with a microfibre mop before applying.

If the existing soil has a high porosity, a second layer must be applied.

Wait 2 to 4 hours before applying Optimum Lacquer. In winter drying time may take longer.



Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

The information included in this data sheet is derived from our knowledge and experience of products. In the light of the wide range of potential uses and forms of application, together with constraints associated with conditions of application or subjective conditions, the data contained herein are provided for information only, and have no legal value. Before any application, it should be checked that the present data sheet has not been superseded by a subsequent version. Version of 16/10/2018. www.harmony-beton.com

HARMONY BETON

235 ZA des Frênes

13109 SIMIANE COLLONGUE

Téléphone : 33 442 20 10 09 Télécopie : 33 442 20 94 17

www.harmony-beton.com