

DATA SHEET

Mortier Ciment colle / Cement Glue

Description

Harmony Cement Glue is based on hydraulic binders modified with additives and high performance resins.

Use as a primer for Harmony Béton Ciré, to fill the joints of the tiles and to create an even, surface / to bring the level back to zero.

Characteristics

Type: Cement Glue

Particle size: 0/0,5mm

Packaging: 4 kg, 10 kg, 20 kg

Adhesion to normalised concrete:> 2,2 MPa

Dosage: 1,8 kg / m² for 10 - 12 m² at a thickness of 1 mm

Drying time: 6 - 8 hours (room temperature); recoatable after 12 hours

Storage: 12 months in unopened original packaging, stored in a dry and frost-free location.

Guarantee: Manufacturer's liability

Compliant with standard NF EN 13813

Tool

stainless steel smoother, sponge, gloves.

Clean tools in water after use.

Preparation

The base surface must be resistant, sound, solid, clean, dry and free of humidity.

Use Harmony Neutral Agent or Harmony Degreaser for any cleaning required (to remove grease, oil etc).

Before applying, prime the floor with Harmony Prime Plus.

Apply the primer evenly, being careful not to leave any spots.

Drying time: 30 minutes to 2 hours, depending on the nature of the substrate and the ambient temperature. Once the primer is dry, the cement glue can be applied.

Application

Harmony Cement Glue is supplied ready for use.

Mix 20 kg of cement paste with 5.5 to 6 litres of water in the mixer for at least 3 minutes.

For 8 kg, mix 2 to 2.4 litres of water.

For 4 kg, mix 1 to 1.2 litres of water.

Apply with the stainless steel smoother on the tiles.

The surface (joint and tiles) must be completely covered.

Smooth well to eliminate all irregularities. Then refine surface with a sponge or spatula.

Do not use in frost conditions.

Drying time: 6 to 8 hours, depending on ambient temperature and humidity.



The information included in this data sheet is derived from our knowledge and experience of products. In the light of the wide range of potential uses and forms of application, together with constraints associated with conditions of application or subjective conditions, the data contained herein are provided for information only, and have no legal value. Before any application, it should be checked that the present data sheet has not been superseded by a subsequent version. Version of 16/10/2018. www.harmony-beton.com

HARMONY BETON

235 ZA des Frênes 13109 SIMIANE COLLONGUE

Téléphone : 33 442 20 10 09 Télécopie : 33 442 20 94 17

www.harmony-beton.com