

## DATA SHEET

# Béton Universel / Beton Universal

### Description

Harmony Béton Universel is a ready-to-use concrete mix that can be used for small repairs.

### Characteristics

Type: concrete mix, dosage based on 300kg

Particle size: 0 - 8 mm

Packaging: 25kg

Compression strength: 40 MPa: after 28 days

Bending strength: 6 MPa: after 28 days

Dosage: 20 kg / m<sup>2</sup> /cm

Storage: 6 months in unopened original packaging, stored in a dry and frost-free location.

Guarantee: Manufacturer's liability

Compliant with standard NF EN 13813

### Application

Ready to use.

Mix a 25 kg bag with 2.5 to 3 litres of clean water in a concrete mixer.

The operating temperature must be between + 5 and + 30 ° C.

To facilitate the making process Harmony softener can be added.

For more resilience, you can also use Harmony thermoplastic fibre



Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

The information included in this data sheet is derived from our knowledge and experience of products. In the light of the wide range of potential uses and forms of application, together with constraints associated with conditions of application or subjective conditions, the data contained herein are provided for information only, and have no legal value. Before any application, it should be checked that the present data sheet has not been superseded by a subsequent version. Version of 16/10/2018. [www.harmony-beton.com](http://www.harmony-beton.com)

HARMONY BETON

235 ZA des Frênes

13109 SIMIANE COLLONGUE

Téléphone : 33 442 20 10 09 Télécopie : 33 442 20 94 17

[www.harmony-beton.com](http://www.harmony-beton.com)