

DATA SHEET

Vernis Effet Mouillé / Wet-Look Lacquer

Description

Harmony Wet-Look Lacquer is a solvent-based varnish that gives the concrete a wet look. This product is particularly suitable for printed or with colour acid treated screed and concrete floors.

Characteristics

Type: One-component polyurethane coating in stabilised solvent phase with U.V protection

Colour: Transparent

Packaging: 1 kg, 4 kg.

Dosage: 1 kg = 10 m² (one coat); the dosage always depends on the porosity of the carrier.

Storage: 12 months in unopened original packaging, stored in a dry and frost-free location.

Guarantee: Manufacturer's liability

Tools & Cleaning

Lacquer roller, paint tray, tarpaulin, gloves, overshoes.

Clean tools in acetone after use.

Preparation

The base surface must be resistant, sound, solid, clean, dry and free of humidity.

Use Harmony Neutral Agent or Harmony Degreaser for any cleaning required (to remove grease, oil etc).

In rainy or wet weather, the concrete must be at least 6 days old or older.

Application temperature: Minimum 10 °, Maximum 25 °.

It is important to respect the temperature guidelines: Excessive heat during the application of the varnish may result in a crust that will not adhere to the surface, which may cause the varnish to peel off.

Application

Apply a thin and even film.

Dose: 1 kg per 10 m², per coat. With a porous underground, the consumption can be higher.

Pay attention to the dose, because if you use too little, white stains or traces of rolling can occur over time.

Drying time: After 2 - 3 hours, another coat can be applied.

For a permanent wet look a second coat is absolutely necessary.

Drying time: walkable after 6 hours, open to traffic after 48 hours.



The information included in this data sheet is derived from our knowledge and experience of products. In the light of the wide range of potential uses and forms of application, together with constraints associated with conditions of application or subjective conditions, the data contained herein are provided for information only, and have no legal value. Before any application, it should be checked that the present data sheet has not been superseded by a subsequent version. Version of 16/10/2018. www.harmony-beton.com

HARMONY BETON

235 ZA des Frênes 13109 SIMIANE COLLONGUE

Téléphone : 33 442 20 10 09 Télécopie : 33 442 20 94 17

www.harmony-beton.com