

## DATA SHEET

# Vernis Hydro / Hydro Lacquer

### Description

Harmony Hydro Lacquer is a water-repellent impregnating agent based on fluorocarbon that protects and beautifies all concrete surfaces in the interior.

### Characteristics

Type: One-component resin emulsion in aqueous phase

Colour: White/transparent

pH: 3-4

Dosage: 1 l = 10 - 12 m<sup>2</sup> per coat

Packaging: 1 l, 5 l, 20 l

Storage: 12 months in unopened original packaging, stored in a dry and frost-free location.

Guarantee: Manufacturer's liability

### Tools & Cleaning

Microfibre mop, broom, gloves, overshoes.

Clean tools in water after use.

### Preparation

The base surface must be resistant, sound, solid, clean, dry and free of humidity.

Use Harmony Neutral Agent or Harmony Degreaser for any cleaning required (to remove grease, oil etc).

The subsurface / existing concrete must be at least 21 days old.

Caution: Check that the floor has not been worked with a curing product. If so, we recommend stripping the existing cure product with Harmony Décap Curing Agent.

### Application

Application temperature: Minimum 10 °, Maximum 25 °.

Avoid draught.

So that the hydro-lacquer does not dry too quickly during the application, it is recommended

to moisten the floor slightly before.

Apply a thin, even film with a microfibre mop.

Pay attention to the dosage: 1 litre per 10 m<sup>2</sup>.

After 2 - 3 hours, a second coat can be applied.

Dosage: 1 litre per 10 m<sup>2</sup>.

Drying time: 24 hours.



The information included in this data sheet is derived from our knowledge and experience of products. In the light of the wide range of potential uses and forms of application, together with constraints associated with conditions of application or subjective conditions, the data contained herein are provided for information only, and have no legal value. Before any application, it should be checked that the present data sheet has not been superseded by a subsequent version. Version of 16/10/2018. [www.harmony-beton.com](http://www.harmony-beton.com)

HARMONY BETON

235 ZA des Frênes 13109 SIMIANE COLLONGUE

Téléphone : 33 442 20 10 09 Télécopie : 33 442 20 94 17

[www.harmony-beton.com](http://www.harmony-beton.com)